



## TIMBERULOVE SIBERIAN LARCH

### GRADE AND QUALITY DESCRIPTION

#### A Grade

---

**Grading Criteria** - *Siberian Larch Cladding, Decking, Fencing*

Hand selected to meet stringent internal criteria.  
Clean, consistent virtually knot free appearance  
Kiln-dried to moisture content of 16-18% (+/- 2%)  
*Graded to GOST 8486-86 A grade*

---

**Wood Fibre** - Slow grown, dense wood from old growth forests in Krasnoyarsk region of Russia

<b>Knots</b>	Permitted	Timber is mostly free of knots. However occasional knots permitted about 30mm in diameter up to 2 knots per linear metre.
<b>Sap Wood</b>	Permitted	Up to 5% sapwood
<b>Deformation (Warp)</b>	Permitted	Slight curvature on occasional boards as far as proper installation ensured
<b>Cracks</b>	Permitted	End cracks permitted no longer than 50mm. Therefore boards supplied are longer to allow pre-cut split or cracked ends
<b>Handling Marks</b>	Permitted	Occasional minor handling marks

<b>Colour Variation</b>	Permitted	Colour can vary between boards and within boards. Typical colour range: dark brown to a pale yellow.
-------------------------	-----------	--

This is offered as a general guide to the main characteristics likely to be encountered in any shipment of A Grade material. There are other minor wood characteristics not listed which may occasionally be present but would not detract from the usability of the material.